

Test Report

No. AJFS2112010301FF

Date: DEC.08, 2021

Page 1 of 4

DOREL HOME FURNISHINGS EUROPE LTD

BUILDING 4, IMPERIAL PLACE MAXWELL ROAD BOREHAMWOOD WD6 1JN UNITED KINGDOM

Product Description: WUXING UKFR VELVET GREY FABRIC

SGS Ref No.: AJHL2112004342OT

Ref. No./Item No.: 002299479UK/ REALROOMS FITZ CHAIR GRY VEL

Buyer: DOREL HOME FURNISHINGS EUROPE LTD

Supplier: ZHEJIANG WUXING FURNITURE CO., LTD

Manufacturer: WUXING FACTORY

Country of Origin: CHINA

Country of Destination: UK

Labeled Age Grading: ADULT

The above sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Test Requested:

The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No.1324 (amended 1989,1993 and 2010), Schedule 4, Part I, Cigarette test for cover fabrics and Schedule 5, Part I, Match test for cover fabrics.

As specified in above standard(s) and incorporated with using ignition source 0 and 1 of BS 5852: Part 1:1979.

Test Results: -- See attached sheet --

Conclusion: The tested sample **Meets** the Requirements of Schedule 4 Part I and Schedule 5 Part I In Statutory Instrument 1988 No.1324 (Amended 1989,1993 and 2010) the Furniture and Furnishings (Fire) (Safety) Regulations.

Test Period:

Sample Receiving Date : DEC.01, 2021
 Test Performing Date : DEC.01, 2021 TO DEC.07, 2021

Signed for and on behalf of
 SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch

Allen Zou
 Approved Signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Test Conducted

The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (amended 1989, 1993 and 2010), Schedule 4 Part I and Schedule 5 Part I, Cigarette test and Match test for cover fabric. Smouldering Cigarette (ignition source 0) and Match Ignition (ignition source 1) of BS 5852:1979 Part 1.

Conditioning

Prior to testing the sample was, Cleansed using a water-soak procedure at 40±1°C as described in BS 5651:1978 and modified by this Regulations 1988 S.I. No. 1324 (amended 1989, 1993 and 2010) Schedule 4 Part I and Schedule 5 Part I. And then dried and conditioned at least 72 h in indoor ambient conditions and 16 h in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%. At time of testing: Temperature between 15°C ~ 30°C and Relative humidity between 20% ~ 70%.

Test results

The following test results relate only to the ignitability of the combination of materials under the particular condition of test. They are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

| | | |
|--|-----------------|-----------------|
| (A) Smouldering cigarette test criteria (BS 5852 Part 1:1979) | 1 st | 2 nd |
| Clause 9.2.3 Whether the evidence of progressive smouldering or flaming is observed in the interior and/or cover | NO | NO |
| Clause 9.2.4 Whether progressive smouldering or flaming of the sample is observed at any time within one hour of placement of the cigarette | NO | NO |
| Clause 9.2.5 Whether progressive smouldering is observed on final examination when dismantle assembly and examine internally | NO | NO |
| (B) Butane flame test criteria (BS 5852 Part 1:1979) | 1 st | 2 nd |
| Clause 9.3.4 Whether the evidence of flaming or progressive smouldering in the interior and/or cover is observed beyond 120s of the removal of the burner tube | NO | NO |
| Clause 9.4 On final examination whether progressive smouldering is observed when dismantle assembly and examine internally | NO | NO |

To be continued....



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Test Details

| Cigarette Test | | | |
|--|----------------------------|-----------------|-----------------|
| Specimen No. | | 1 st | 2 nd |
| Progressive smouldering (PS) or Flaming (F) | | NO | NO |
| Duration of | Ignition source (min, sec) | 24min09s | 23min40s |
| | Flames (min, sec) | 0s | 0s |
| | Smoke (min, sec) | 24min21s | 23min47s |
| Final examination of progressive smouldering (9.4) | | NO | NO |
| Reason for failure (Ref to failure code) | | -- | -- |
| Comments & observations | | -- | -- |
| Overall Result | | PASS | PASS |

| Match Test | | | |
|--|-----------------------------|-----------------|-----------------|
| Specimen No. | | 1 st | 2 nd |
| Progressive smouldering (PS) or Flaming (F) | | NO | NO |
| Duration of | Ignition source (19-21 sec) | 20s | 20s |
| | After flames (min, sec) | 0 | 0 |
| | Smoke (min, sec) | 28s | 26s |
| Final examination of progressive smouldering (9.4) | | NO | NO |
| Reason for failure (Ref to failure code) | | -- | -- |
| Comments & observations | | -- | -- |
| Overall Result | | PASS | PASS |

Remark: The submitted sample was tested in combination with standard worse case scenario non-flame retardant conventional polyurethane foam as specified in the Regulations.

Statements:

The declaration of conformity is based on non-binary acceptance decision rules with guard band, and the guard band length parameter is 0.

To be continued....



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Photo Appendix:

Details of sample:

Color: Grey

This fabric sample of approximate density of 443 g/m².



SGS authenticate the photo on original report only

*** End of Report **