



Test Report

Report No.: AJFS2401001059FF

Date: FEB.01, 2024

Page 1 of 4

DOREL HOME FURNISHINGS EUROPE LTD

ALPHASON HOUSE, 244 SWAN LANE, HINDLEY GREEN, WIGAN WN2 4EY, UNITED KINGDOM

Product Description: UKFR - PU BLACK

SGS Ref No.: AJHL2401000414FT

Ref. No/Item No.: DAYTONA RACING CHAIR – BLACK/DRAKE RECLINER & FOOTSTOOL-BLK
DRAKE RECLINER & FOOTSTOOL-BLK

Supplier: ANJI SHENGXING OFFICE FURNITURE

Buyer: DOREL HOME EUROPE

Manufacturer: SHENGXING FACTORY

Country of Origin: CHINA

Country of Destination: GREAT BRITAIN

Labeled Age Grading: ADULT

The above sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Test Requested:

The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No.1324 (amended 1989,1993 and 2010), Schedule 4 Part I Cigarette test for cover fabrics and Schedule 5 Part I Match test for cover fabrics. As specified in above standard(s) and incorporated with using ignition source 0 and 1 of BS 5852 Part 1:1979.

Test Results: -- See attached sheet --

Conclusion: The tested sample **Meets** the Requirements of Schedule 4 Part I and Schedule 5 Part I in Statutory Instrument 1988 No.1324 (Amended 1989,1993 and 2010) the Furniture and Furnishings (Fire) (Safety) Regulations.

Test Period:

Sample Receiving Date : JAN.25, 2024

Test Performing Date : JAN.25, 2024 TO JAN.31, 2024

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch

Echo

Echo Li
Approved Signatory

Scan to see the report



AJFS2401001059FF
Verification:
check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

Test Report

Report No.: AJFS2401001059FF

Date: FEB.01, 2024

Page 2 of 4

Test Conducted

The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (amended 1989, 1993 and 2010), Schedule 4 Part I Cigarette test for cover fabrics and Schedule 5 Part I Match test for cover fabrics. Smouldering cigarette test(ignition source 0) and Butane flame test(ignition source 1) of BS 5852 Part 1:1979.

Conditioning

The specimens were cleansed using a water-soak procedure at 40±1°C as described in BS 5651:1978 and modified by this Regulations 1988 S.I. No. 1324 (amended 1989, 1993 and 2010) Schedule 4 Part I and Schedule 5 Part I.

The specimens were conditioned immediately before the test for 72 h in indoor ambient conditions and then for at least 16 h in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%.

At time of testing: Temperature between 15°C ~ 30°C and Relative humidity between 20% ~ 70%.

Test Result

The following test results relate only to the ignitability of the combination of materials under the particular condition of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

(A) Smouldering cigarette test criteria (BS 5852 Part 1:1979)	1 st	2 nd
Clause 9.2.3 Whether the evidence of progressive smouldering or flaming is observed in the interior and/or cover	No	No
Clause 9.2.4 Whether progressive smouldering or flaming of the sample is observed at any time within one hour of placement of the cigarette	No	No
Clause 9.2.5 Whether progressive smouldering is observed on final examination when dismantle assembly and examine internally	No	No
(B) Butane flame test criteria (BS 5852 Part 1:1979)	1 st	2 nd
Clause 9.3.4 Whether the evidence of flaming or progressive smouldering in the interior and/or cover is observed beyond 120s of the removal of the burner tube	No	No
Clause 9.4 On final examination whether progressive smouldering is observed when dismantle assembly and examine internally	No	No



Test Report

Report No.: AJFS2401001059FF

Date: FEB.01, 2024

Page 3 of 4

Detailed Results

Cigarette Test			
Test No.		1 st	2 nd
Progressive smouldering (PS) or Flaming (F)		No	No
Duration of	Ignition source (min, s)	2 min 05 s*	2 min 40 s*
	Flames (min, s)	0 s	0 s
	Smoke (min, s)	2 min 18 s	2 min 49 s
Final examination of progressive smouldering (9.4)		No	No
Reason for failure (Ref to failure code)		--	--
Comments & observations		No	No
Result		Pass	Pass

*--The cigarette self-extinguished

Match Test			
Test No.		1 st	2 nd
Progressive smouldering (PS) or Flaming (F)		No	No
Duration of	Ignition source (19-21 s)	20 s	20 s
	After flames (min, s)	0 s	0 s
	Smoke (min, s)	33 s	29 s
Final examination of progressive smouldering (9.4)		No	No
Reason for failure (Ref to failure code)		--	--
Comments & observations		No	No
Result		Pass	Pass

Remark: The submitted sample was tested in combination with standard worse case scenario non-flame retardant conventional polyurethane foam as specified in the Regulations.

Statement: The decision rules for statements of conformity (Pass/Fail) have been applied to any results that results in a numerical value and are based on the probability conformance of 95% (UKAS LAB 48) agreed with the customer at the contract review stage.



Test Report

Report No.: AJFS2401001059FF

Date: FEB.01, 2024

Page 4 of 4

Photo Appendix:

Details of sample:

Color: Black

This PU sample of approximate area density of 477 g/m².



SGS authenticate the photo on original report only

*** End of Report **